# To protect the privacy of customers or suppliers of Salamander Jewelry. We erased their address from this document.

## **Quality Certificate**

No.: PO 2330364 - dia 8.0mm

-	-	•	. •
- 1	Desc	rini	hon.
	17556	1 117	11()11
• •			UI CII.

Commodity	Material	Standard	Condition	
Ti-6Al-4V ELI Bar	Ti-6Al-4V ELI	ASTM F136	Annealed	
Heat No.	Lot No.	Size	Weight	
20199911	20011203	Ø8.0*2000mm	0.90Kgs(2pcs)	

#### 2. Chemical Composition (Wt%):

Element	Ti	Al V	Ea	С	N	О	11	Others		
Element			v	Fe		17		Н	Each	Total
Pag		5.5	3.5							
Req (Max.)	Bal	-	-	0.25	0.08	0.05	0.13	0.012	0.10	0.40
		6.5	4.5							
Results	Bal	6.10	4.03	0.173	0.018	0.010	0.084	0.0007	< 0.1	< 0.4
Results	Bal	6.01	3.89	0.128	0.018	0.010	0.102	0.0008	< 0.1	< 0.4

#### 3. Mechanical Properties:

Test Items	Tensile Strength Rm [Mpa]	Yield Strength Rp0.2 [Mpa]	Elongation A [%]	Area of Reduction Z [%]
Requirements	≥860	≥795	≥10	≥25
Results	964	886	17.0	46

#### 4. Other Test Items:

Microstructure	Ultrasonic	Dimensional	Visual	Surface	
Whetostructure	Test	Inspection	Inspection	Contamination	
Qualified	Qualified	Qualified	Qualified	Clean	

### 5. Conclusion and Statement:

We hereby certify that these Titanium Ti-6Al-4V ELI bars/rods herein has been manufactured, sampled, tested, and inspected in accordance with ASTM F136 and other specified requirements of PO 2330364, and met these requirements.

Inspected by	Prepared by	Approved by
Michelle Zhang	Jimmy Liu	Jianyin Xu
Jan.28 <sup>th</sup> , 2021.	Jan.28 <sup>th</sup> , 2021.	Jan.28th, 2021.

#### **END OF REPORT!**