

To protect the privacy of customers or suppliers of Salamander Jewelry.  
We erased their address from this document.

## REPORT OF ANALYSIS

Ref.No. :

SCM-206

Date

23-Nov-58

Certificate of Analysis

Origin : Hong Kong

We have finished the analysis of silver sample received on 25 October 2015 the results are as following:

### 1. Silver Content

Our ref.	Before melt	After melt	Lab	Customer	Ag %	Fine silver
298317G6	18.30	18.30	-	-	99.99	18.298
298317G7	18.10	18.10	-	-	99.99	18.098
Total			-	-	-	

### 2. Au, Bi, Cd, Cu, Fe, Mg, Ni, Pb, Sb, Se, Te, Zn content of the silver sample

Our ref.	Au	Bi	Cd	Cr	Cu	Fe	Mg	Ni	Pb	Pd	Sb	Se	Te	Zn
298317G6	1.6	-	-	-	1.8	3.7	-	-	2.1	18.60	-	-	-	-
298317G7	1.8	-	-	-	9.1	3.6	-	-	-	-	-	-	3.6	-

\*\* Unit of above table: ppm

To protect the privacy of customers  
or suppliers of Salamander Jewelry.  
We erased their address  
from this document.